



Capriana vinyl pairs contemporary colours and texture along with a modern and durable construction that is pliable to work with. Designed and crafted as one of the best in class for the commercial vinyl industry to meet the standards of artistry, craftsmanship while providing long term comfort and performance. As a marine vinyl, it is mildew and bacteria resistant, UV stabilized, and designed for use in the elements. Capriana can be heat-sealed for water-tight seams, and offers superior stretch for wrapping around corners and curves.

Industries & Markets

- Corporate Office
- Food Service
- Healthcare
- Hospitality & Entertainment
- Retail
- Marine

End-Use Applications

- Contract Seating
- Dining Seating
- Medical Furnishings
- Guest room furnishings
- Spas & Health Clubs
- Theater Seating
- Retail Seating
- Interior Surfaces
- Boats and Personal Watercraft

Physical Specifications

| | |
|------------------------|------------------------|
| Weight (ASTM D 751 79) | 30 oz/lin yd |
| Width (CFFA-700a) | 54 in. [137 cm] |
| Face Composition | PVC |
| Backing Description | Woven Polyester |
| Roll Size | 30 lin yd [27.4 lin m] |
| Emboss Level | Light |
| Thickness | 0.9mm |

Flame, Smoke & Toxicity

Meets or exceeds the following:

- Cal Tech 117 Section 3
- FMVSS 302
-

Performance Features

| | |
|--------------------------------------|--|
| Protective Finish | MicroSheild |
| Use | Outdoor/Indoor |
| Tear Strength (ASTM D 751) | 6 Warp, 6 Fill (lbs) |
| Tensile Strength (ASTM D 751) | 80 Warp, 90 Fill (lbs) |
| Wyzenbeek Abrasion (#10 Cotton Duck) | 50,000 (double rubs) |
| Trap Tear Strength #, min (CFFA-16c) | 38 Warp, 38 Fill |
| Cold Crack (ASTM D 191A-5874) | -10 °F [-23 °C] |
| QUV-B 500 Hours | Pass |
| Oil/Sulfide Resistance | Pass |
| Fungal Resistance (ASTM-G-21) | Pass (including ASTM E1428) (Pink Stain) |
| Bacterial Resistance | Pass |
| Weatherometer | 1500 Hours |

Revision Date: 1-Feb-21

Note: Due to possible variances in your computer monitor, the colors and patterns displayed may vary slightly from the actual product. Customers should always obtain and compare actual samples before specifying.



Distributed by:
Textile House
www.textilehouse.co.nz
100 John Street
Pukekohe 2120
New Zealand
P | 0800 644 445
F | 0800 65 99 00